

# Electronic **BALVER ZINN**<sup>®</sup>

## Technical Data Sheet

### BALVER ZINN SOLDER

#### Sn63b37

#### General Information

**BALVER ZINN SOLDER Sn63Pb37** is a standard tin lead solder alloy for wave and selective soldering. **BALVER ZINN SOLDER Sn63Pb37** can also be used also dip tinning.

Technical information and Data Sheets can be found on our website ([www.BALVERZINN.com](http://www.BALVERZINN.com)). You can also obtain all information and documents directly from **BALVER ZINN**.

#### BALVER ZINN Production Programme

The **BALVER ZINN** production programme also includes solder bar, solder pastes and flux. In addition to the **SN100C** product family, **BALVER ZINN** offers additional unpatented and patented solder alloys for wave soldering, reflow and rework.

#### Physical properties of Sn63Pb37

Melting point °C	183
Specific Gravity g/cm <sup>3</sup>	8.4

#### Composition of Sn63Pb37

Element	Sn63Pb37E According to ISO 9453: 2006 in weight- %
Sn	63 +/- 0.5
Pb	Remainder
Al	max. 0.01
As	max. 0.03
Bi	max. 0.05
Cu	max. 0.08
Cd	max. 0.002
Fe	max. 0.02
Ag	max. 0.1
Sb	max. 0.05

#### Delivery size

Format	L in mm	B in mm	H in mm	
Ingots	1 kg	325	28	15
	4 kg	300	50	40
Ingots with hole	3,7 kg	540	50	20
	6 kg	570	48	35
Bar 1 kg	325	28	15	
Pellet	12 x 25			
Wire, solid on reel	Ø 1.0 – 6.0			

#### Storage Conditions / Durability

Dry storage at room temperature / minimum 2 years

#### Safety Advice

Before using please refer to the appropriate Safety Data Sheet.

Although the information in this data sheet is considered accurate, the measured values do not represent assured properties or delivery specifications. Because of the wide range of potential materials and applications, and with respect to possible protective rights and third parties, Balver Zinn Josef Jost GmbH & Co. KG **cannot** accept any liability.

#### **OUR GLOBAL DISTRIBUTION NETWORK**

##### **Balver Zinn Josef Jost GmbH & Co. KG**

Balve; Germany

☎: +49 2375 915 0

✉: [cia@balverzinn.com](mailto:cia@balverzinn.com)

✓: [www.balverzinn.com](http://www.balverzinn.com)

##### **Cobar Europe BV**

Breda; The Netherlands

☎: +31 76 544 55 66

✉: [info@cobar.com](mailto:info@cobar.com)

✓: [www.cobar.com](http://www.cobar.com)

##### **Cobar Solder Products Inc.**

Little River; USA

☎: +1 (843) 734 1491

✉: [info.usa@cobar.com](mailto:info.usa@cobar.com)

✓: [www.cobar.com](http://www.cobar.com)